

# Cadmium Free SilverAlloy A-35

Aufhauser Corporation 39 West Mall Plainview, NY 11803 Telephone: 516-694-8696 800-645-9486 Fax: 516-694-8690

### **+ INTRODUCTION**

Aufhauser SilverAlloy A-35 is a good general purpose brazing alloy used for most metals except aluminum and magnesium.

#### **APPLICATIONS**

SilverAlloy A-35 is suitable in the joining of ferrous, nonferrous and dissimilar metals and alloys with close joint clearances. It is a good choice for brazing in the dairy and food industries where the use of cadmium is prohibited. It is also often used in the electrical industry and for brazing brass parts such as ships' piping, band instruments, lamps, etc.

#### **+ CHEMICAL COMPOSITION**

<u>Silver</u> <u>Copper</u> <u>Zinc</u> 34.0-36.0 31.0-33.0 31.0-35.0

### **♦ PHYSICAL and MECHANICAL PROPERTIES**

Solidus: 1260 °F
Liquidus: 1370 °F
Brazing Range: 1370-1545°F
Specific Gravity: 8.66
Density: 4.56 TO/cu. in.
Electrical Conductivity: 22.0 %IACS
Color: Yellow White



## **♦ SPECIFICATIONS MEET or EXCEED**

- AWS A5.8 BAg-5

- ISO 3677: B Ag 35 Zn Cu 680-750

## **+ STANDARD SIZES AND DIAMETERS**

- Diameters: 1/32", 3/64", 1/16", 3/32", 1/8"

- Sizes: 1, 3, 5, or 50 troy ounce

## **♦ PROPERTIES OF BRAZED JOINTS**

Generally, the joint strength using SilverAlloy A-35 will surpass the strengths of the base metals. Strength is a function of the base metals being joined, type of joint, design of joint, joint clearances and brazing procedures. The recommended maximum operating temperature for SilverAlloy A-35 is up to 400°F in continues service and up to 600°F in intermittent services. For improved corrosion resistance, SilverAlloy A-50Ni2 and SilverAlloy A-40Ni2 are recommended.