

Flux Coated Cadmium Free SilverAlloy A-35FC

Aufhauser Corporation 39 West Mall Plainview, NY 11803 Telephone: 212-246-0205 800-645-9486 Fax: 212-246-0158 sales@brazing.com

INTRODUCTION

Aufhauser SilverAlloy A-35FC is a cadmium-free filler metal used for brazing ferrous and nonferrous base metals. It is a moderate temperature filler metal frequently used for production brazing applications. A-35FC is pre-fluxed with the correct amount of flux. No dipping or preparatory work. Suitable for work in tight places.

APPLICATIONS

Aufhauser A-35FC is used for joining most ferrous and non-ferrous metals.

CHEMICAL COMPOSITION

SilverCopperZinc34.0-36.031.0-33.031.0-35.0

♦ PHYSICAL and MECHANICAL PROPERTIES

Solidus	
Liquidus	1390 °F (754 °C)
Brazing Range	1390-1545°F (754-841 °C)
Specific Gravity	8.87
Density	4.67 TO/cu. in.
Electrical Conductivity	19.8 %IACS
Color	Yellow White



♦ SPECIFICATIONS MEET or EXCEED

- AWS A5.8 BAg-35
- ISO 3677: B Ag 35 Zn Cu 680-750
- UNS P07351
- EN 17672 Ag 235

• AVAILABLE FORMS

- Powder/Paste
- Wire, Rods, Foil
- Specialty preforms per customer specifications

♦ PROPERTIES OF BRAZED JOINTS

STANDARD ROD SIZES AND DIAMETERS
Diameters: 1/22// 2/64// 1/16// 2/22// 1/

- Diameters: 1/32", 3/64", 1/16", 3/32", 1/8"
- Sizes: 1, 3, 5, or 50 troy ounces
- Lengths: 18, 20, or 36 inches

Generally, the joint strength using SilverAlloy A-35FC will surpass the strengths of the base metals. Strength is a function of the base metals being joined, type of joint, design of joint, joint clearances and brazing procedures.