

Cadmium Bearing SilverAlloy Cd-35

◆ INTRODUCTION

Aufhauser SilverAlloy Cd-35 is a modification of SilverAlloy Cd-45 to combine reasonable good brazing properties and lower silver content at the expense of slight elevated temperature (150°F). It has a broader melting range than Cd-45, which is helpful where clearances are wide or not uniform. Unless heating is rapid, care must be taken that the lower melting constituents do not separate out by liquidation. Cd-35 is free-flowing and suited for general purpose work. *This filler metal contains cadmium.*

◆ APPLICATIONS

Aufhauser Cd-35 is used for joining most ferrous and non-ferrous metals. Cd-35 has good brazing properties and is suitable either for pre-placement in the joint or for manual feeding into the joint. Although lap joints generally are used, butt joints may be used if requirements are less stringent. Joint clearances of 0.001 to 0.005 in. (0.025 to 0.13) are recommended for proper capillary action.

◆ CHEMICAL COMPOSITION

<u>Silver</u>	<u>Copper</u>	<u>Zinc</u>	<u>Cadmium</u>
34.0-36.0	25.0-27.0	19.0-23.0	17.0-19.0



◆ PHYSICAL and MECHANICAL PROPERTIES

Melting Point:	1125 °F
Density:	4.84 TO/Cu.In.
Color, as brazed:	Light Yellow

◆ SPECIFICATIONS MEET or EXCEED

- AWS A5.8 BAg-2
- AMS 4768D, Class BAg-2
- QQ-B-654A, Type VIII
- ISO 3677: B Ag 35 Cd Zn Cu 610-700
- NFA 81-362, 35 A1

◆ STANDARD SIZES AND DIAMETERS

- Diameters: 1/32", 3/64", 1/16", 3/32", 1/8"
- Sizes: 1, 3, 5, or 50 troy ounce

Caution! Contains cadmium. Fumes are poisonous and can kill.

Provide adequate ventilation and do not inhale gases and fumes. Read and understand American National Standard Z49.1, "Safety in Welding and Cutting", available from:

American Welding Society,
550 N.W LeJeune Road, P.O. Box 351040, Miami, Florida 33135.