## APPLICATIONS

INTRODUCTION

Welding steels with dirty or rusty surface

- (UNS numbers K02600, K02801, K02001, K02700)
- Single-pass welding of killed, semi-killed, and rimmed steels, but may be used for some multi-pas applications.

### CHEMICAL COMPOSITION

(AWS A5.18, Typical)

Ca	arbon Ma	inganese	Silicon	Phosphorus	Sulfur	
Nominal .1	0 1.	15	.60	.025	.035	
Note: All values are maximum percentage, unless shown in range.						

# PHYSICAL and MECHANICAL PROPERTIES

Tensile Strength:	81,000 psi
Yield:	67,900
Elongation, min. %:	29
Average Impact Strength%:	29

#### SPECIFICATIONS MEET or EXCEED

ANSI/AWS A5.18 (ER 70S3)

## STANDARD SIZES AND DIAMETERS

Diameters 0.23", 0.30", 0.35", 0.45"

Properties were determined with 100% CO2 shielding gas.

MILD STEEL MIG WIRE

AUFHAUSER 70S-3 is a silicon and manganese deoxidized wire used for mild and low alloy steel general purpose fabrication. A well balanced silicon and manganese content permits its use with CO2, Argon-Oxygen mixtures, or mixtures of the two. This wire may be used for short-circuiting arc (dip-transfer), buried arc, as well as spray transfer arc processes.

70S-3





Aufhauser Corporation 39 West Mall Plainview, NY 11803 Telephone: 516-694-8696 800-645-9486 Fax: 516-694-8690