



## SilverAlloy A-59Ti-Active

Aufhauser  
Corporation  
39 West Mall  
Plainview, NY 11803  
Telephone:  
516-694-8696  
800-645-9486  
Fax: 212-246-0158  
sales@brazing.com

### Introduction

Aufhauser SilverAlloy A-59Ti-Active is an active, brazing alloy that promotes wetting and good capillary action on several surfaces that would otherwise be difficult to join by brazing. The active components of this alloy promote wetting on, for example, ceramics, aluminum oxides (sapphire), diamond.

### Applications

Brazing with Aufhauser SilverAlloy A-59Ti-Active provides a reliable method of bonding ceramics to any metals (including stainless steels).

### Nominal Composition

Ag %	Cu %	In %	Ti %
59.0	27.25	12.5	1.25

### Physical Properties \*

Parameter	In US units	In metric units
Solidus temperature	1121 °F	605 °C
Liquidus temperature	1319 °F	715 °C
Recommended brazing temperature	1319 – 1364 °F	715 – 740 °C
Recommended brazing atmosphere	10 <sup>-5</sup> mm Hg vacuum or inert gas	10 <sup>-5</sup> mm Hg vacuum or inert gas
Density	0.35 Lb/in <sup>3</sup>	9.7 g/cm <sup>3</sup>
Thermal expansion coefficient	10.1 x 10 <sup>-6</sup> /°F (R.T. -752°F)	18.2 x 10 <sup>-6</sup> /°C (R.T. -400°C)
Thermal conductivity	40 BTU/ ft <sup>2</sup> x hour x °F	70 W/m x °K
Electrical resistivity	-	10.6 x 10 <sup>-8</sup> ohm-m
Electrical conductivity	-	9.4 x 10 <sup>6</sup> ohm-m
Young's modulus	11 x 10 <sup>6</sup> Lb/in <sup>2</sup>	76 GPa
Ultimate tensile strength	66 x 10 <sup>3</sup> Lb/in <sup>2</sup>	455 Mpa
Yield strength (0.2% offset)	49 x 10 <sup>3</sup> Lb/in <sup>2</sup>	338 Mpa
Elongation (2in/50mm gage section)	21%	21%
Poisson's ratio	0.36	0.36

\* The above properties apply to the alloy before it is used in the brazing process.

**Supplied forms:** foil, wire, paste.