

Cadmium Free SilverAlloy A-50 T

◆ **INTRODUCTION**

Aufhauser SilverAlloy A-50T is similar to A-56T at the expense of increased melt temperature and range.

◆ **APPLICATIONS**

- Aufhauser 50T is used for joining most ferrous and non-ferrous metals.

◆ **CHEMICAL COMPOSITION**

<u>Silver</u>	<u>Copper</u>	<u>Zinc</u>	<u>Tin</u>
50.0	22.0	25.0	3.0

◆ **PHYSICAL and MECHANICAL PROPERTIES**

Melting Point:	1190°F
Density:	4.80 TO/ cu. in.
Color, as brazed:	Pale Yellow



◆ **SPECIFICATIONS MEET or EXCEED**

- Aufhauser Internal

◆ **STANDARD SIZES AND DIAMETERS**

- Diameters: 1/32", 3/64", 1/16", 3/32", 1/8"
- Sizes: 1, 3, 5, or 50 troy ounce